

# The Compressive Strength Of Concrete Using Kakawate (*Gliricidia Sepium*) Jacq. Kunth Ex Walph. Wood Ash Cement

ALFREDO R. RABENA

NELIA V. AMAN

FRANKLYN T. AMISTAD

*alfredorabena@yahoo.com*

R&D, University of Northern Philippines  
Vigan City, Ilocos Sur Philippines

**Abstract** - The acceptable disposal waste such as ash and sludge is a growing problem. A related problem is the recycling of other waste materials such as tires, glass and plastics. Because of the high-volume of kakawate tree in the region and that ash of kakawate wood is considered waste taken from dirty kitchen of every household, the researchers as engineers are pressured to recycle the ash for admixture construction material for low-cost housing projects. The researchers developed a methodology for determining the compressive strength of concrete cylinder mixed with kakawate (*Gliricidia sepium*) Jacq. Kunth ex walph using the proportion 20% ash and 80% cement for the mixture 1:2:3. The result of the laboratory testing can be a basis in proceeding with other proportions. Information is needed about the wood material's

physical properties. Further, environmental and waste management issues must be discussed as basis for the acceptability and practicability of waste and recycled material (WRMs). Developed mixture design of kakawate ash and cement ratio is to be recommended for construction of low-cost housing projects without sacrificing the strength of the structure.

*Keywords* - compressive strength, kakawate

## INTRODUCTION

Concrete is the only major building material that can be delivered to the job site in a plastic state. This unique quality makes concrete desirable as a building material because it can be molded to virtually any form or shape. Concrete provides a wide latitude in surface textures and colors and can be used to construct a wide variety of structures, such as highways and streets, bridges, dams, large buildings, airport runways, irrigation structures, breakwaters, piers and docks, sidewalks, silos and farm buildings, homes, and even barges and ships.

The two major components of concrete are a cement paste and inert materials. The cement paste consists of portland cement, water, and some air either in the form of naturally entrapped air voids or minute, intentionally entrained air bubbles. The inert materials are usually composed of fine aggregate, which is a material such as sand, and coarse aggregate, which is a material such as gravel, crushed stone, or slag.

It is a known fact that the cost of commercial cement is increasing. Thus alternative materials or admixture to reduce the quantity of cement in concrete while maintaining its strength, need to be studied.

Admixtures are developed specifically to provide better performance benefits to concrete. It can be used to reduce cement content and allow additional pozzolanic materials--fly ash, silica fume, and ground granulated blast-furnace slag--to be incorporated to extend production capacity, helping producers optimize the cement content of their mixes. It is effective in producing concrete mixtures with different levels of workability, including applications that require

using self-consolidating concrete. Several researches were conducted on the effect of these admixtures to concrete. Study on the use of fly ash has proven to have a positive effect on concrete. Derived from burning coal, fly ash is a valuable additive that makes concrete stronger, more durable and easier to work with. The cement with flyash or the so called pozzolanic is already out in the market. Another study is the Rice Husk Ash which is used as pozzolana to replace ordinary Portland cement or as admixture and was found to have better resistance to acidic attack.

Most people in the rural areas are still using clay stove for cooking. The firewood being used by most is the kakawate wood because of its abundance in the locality. Kakawate is referred to as a quick-stick due to its characteristic of growing almost right away just by cutting it and directly planting it in the ground. It is a fast growing tree with a maturity height of 10 meters (33 feet). It is adaptable to almost any soil environment, including infertile soils. It is tolerant to salt spray and water logging. It can tolerate drought for up to 6 to 8 months. The tree is common in the southern Tagalog areas, shedding leaves around December and flowering February and March. The wood being hard and durable is used for small housing needs, posts, implement handles and firewood.

### *Significance of the Study*

Concrete which is a combination of cement and aggregates is the most commonly used construction materials for buildings. Cement as one of the components is the most expensive ingredient of concrete and the cost is increasing. The use of additional material to concrete can reduce the cost of concrete.

The researchers were prompted to conduct a study on the Kakawate Wood Ash as admixture to concrete because the cost of production is cheaper, these can only be taken from the dirty kitchen of every household. Instead of throwing these ashes, these can be utilized as admixture to cement. When these Kakawate Wood ash is mixed to an Ordinary Portland Cement and was able to reach the desired compressive strength of concrete, this can be beneficial. It will not only

reduce the cost of concrete but it will also be a source of income to those housewives using clay stove for cooking.

### *Review of Related Literature*

Concrete is an artificial engineering material made from a mixture of portland cement, water, fine and coarse aggregates, and a small amount of air. It is the most widely used construction material in the world. The two major components of concrete are cement paste and inert materials. The cement paste consists of portland cement, water, and some air either in the form of naturally entrapped air voids or minute, intentionally entrained air bubbles. The inert materials are usually composed of fine aggregates, such as sand, and coarse aggregates, such as gravel, crushed stone, or slag. In general, fine aggregate particles are smaller than 6.4 mm (.25 in) in size, and coarse aggregate particles are larger than 6.4 mm (.25 in). Depending on the thickness of the structure to be built, the size of coarse aggregate particles used can vary widely. In building relatively thin sections, a small size of coarse aggregate, with particles about 6.4 mm (.25 in) in size, is used. At the other extreme, aggregates up to 15 cm (6 in) or more in diameter are used in large dams. In general, the maximum size of coarse aggregates should not be larger than one-fifth of the narrowest dimensions of the concrete member in which it is used. (Microsoft ® Encarta, 2006.)

American Concrete Institute (1984) states that an admixture to be used in concrete shall be capable of maintaining essentially the same composition and performance throughout the work as the product used in establishing concrete proportions in accordance with selection of concrete proportions. It is any material other than the basic components of concrete which is used as an ingredient of concrete to modify its properties and to enhance its capabilities. This can be air-entraining admixtures, water-reducing admixtures, retarding admixtures, and water-reducing and accelerating admixtures. Fly ash or other pozzolans are one of the few admixtures used in concrete.

Derived from burning coal, fly ash is a valuable additive that makes concrete stronger, more durable and easier to work with. Fly ash sources in 30 states are linked to a nationwide network of terminals

and transportation equipment - ensuring customers receive quality material when they need it. With nearly 20 million tons of ash products under management annually, Headwaters Resources offers concrete producers the support they need to make ash a part of their every day production. In addition to unparalleled customer service, Headwaters maintains its own extensive laboratory and engineering capabilities. Highly qualified chemists, materials scientists and engineers are on hand to ensure product quality and assist in solving challenges faced by individual customers.

### *Enhancing Concrete Workability*

The difference between fly ash and portland cement is apparent under a microscope. Fly ash particles are smaller and almost totally spherical in shape, allowing them to fill voids, flow easily, and blend freely in mixtures.

Additionally, when water is added to portland cement, it creates two products: a durable binder that glues concrete aggregates together and free lime. Fly ash reacts with this free lime to create more of the desirable binder.

**The “ball-bearing” effect of fly ash particles creates a lubricating action when concrete is in its plastic state. This creates benefits in:**

**Workability.** Concrete is easier to place with less effort, responding better to vibration to fill forms more completely.

**Ease of Pumping.** Pumping requires less energy and longer pumping distances are possible.

**Improved Finishing.** Sharp, clear architectural definition is easier to achieve, with less worry about in-place integrity.

**Reduced Bleeding.** Fewer bleed channels decrease permeability and chemical attack. Bleed streaking is reduced for architectural finishes.

**Reduced Segregation.** Improved cohesiveness of fly ash concrete reduces segregation that can lead to rock pockets and blemishes.

### *Scope and Limitation of the Study*

The scope of the study covered the testing of strength of a concrete with kakawate ash at age 28 days using the proportion 1:2:3 (1 bag kakawate ash cement, 2 boxes sand, 3 boxes gravel). The kakawate ash cement is proportioned as 80% Portland Cement and 20% Kakawate Wood Ash.

### **OBJECTIVE OF THE STUDY**

The study aimed to determine the compressive strength of concrete with kakawate ash cement. It specifically sought to find out the following objectives:

What is the compressive strength of Kakawate Wood Ash Cement using the following proportion:

- a. 80% Portland Cement and 20% Kakawate Wood Ash?

### **MATERIALS AND METHODS**

This section presents the research design, sample, data gathering procedure.

**Research design.** This study utilized the descriptive method. Out of the data gathered, findings were summarized, analyzed, and interpreted.

**Sample.** The samples used in this study are three pieces. concrete cylinder with used kakawate wood ash at age 28 days. The kakawate wood ash were taken from the dirty kitchen of a selected household.

**Procedure.** Three samples of concrete cylinder were taken on the same mixture of concrete and after 24 hours these specimens were soaked in water and cured for 28 days.

After 28 days the three samples for each mixture were brought to BIP Geotechnical and Materials Testing Engineers, an accredited testing laboratory by the Department of Public Works and Highways and tested for compressive strength using the Universal Testing Machine. The average compressive strength were computed and used as basis for analysis.

### RESULTS AND DISCUSSION

Table 1 shows the strength of concrete with kakawate wood ash in terms of compression at age 28 days

It can be seen from the table that the average compressive strength of concrete with kakawate wood ash is 5.47 MPa. Since concrete, other than fill, should have a minimum ultimate compressive strength at 28 days of 140 kilograms per square centimeter (2,000 lbs. per sq.in.)” or 13.82 MPa, the concrete with kakawate wood ash did not reached the required compressive strength.

Table 1. Compressive strength of concrete with kakawate wood ash at age 28 days

Specimen	Compressive Strength (MPa)
1	5.18
2	5.66
3	5.58
Average Compressive Strength, MPa	5.47

## CONCLUSIONS

Based on the results of the study, this conclusion is drawn:

1. The compressive strength of concrete with kakawate wood ash using the proportion 80% Portland Cement and 20% Kakawate Wood Ash is below the accepted compressive strength used in designing structures.

## RECOMMENDATIONS

1. Concrete with kakawate wood ash using the proportion 80% Portland Cement and 20% Kakawate Wood Ash cannot be used for building construction because it did not reach the minimum requirement of compressive strength set by the National Building Code which is equal to 13.82 MPa.
2. Parallel studies can be conducted to determine the strength of concrete with kakawate wood ash cement using various proportions of cement and kakawate wood ash.

## LITERATURE CITED

American Concrete Institute,  
1984. *Building Code Requirements for Reinforced Concrete*, (ACI 318M-83).

Microsoft ® Encarta ® 2006. © 1993-2005 Microsoft Corporation.

Pursuant to the international character of this publication, the journal is indexed by the following agencies: (1)Public Knowledge Project, a consortium of Simon Fraser University Library, the School of Education of Stanford University, and the British Columbia University, Canada; (2) E-International Scientific Research Journal Consortium; (3) Philippine E-Journals; and (4) Google Scholar.

